

# Gafast Pigment Yellow 151


Chemical Class : Benzimidazolone

Chemical Structure:

C.I.Name : Pigment Yellow 151

C.I. No. : 13980

Greenish yellow pigment with excellent fastness to light & weathering. Mainly suitable for Automotive paints, Printing Inks, Plastic Coloration.



Full Shade

## Product specification:

Physical Data:

Physical form

Powder

Specific Surface Area (BET), (m<sup>2</sup>/g)

11 – 13

Average Particle size, (μm)

≅ 0.239

Oil Absorption Value, (g/100g)

45.56

pH of 10% extract

6.0 – 8.0



Reduction  
1:16 TiO<sub>2</sub>

## Resistance to Solvents:

Water	5
Mineral Turpentine oil	5
n-Butanol	5
Xylene	4 - 5
Butyl Acetate	5
MEK	4 - 5

## Heat Stability:

240°C

Weather fastness:


	Full shade	Reduction
Alkyd/melamine	4 - 5	4 - 5
Acrylic/melamine	4 - 5	4 - 5
Air-drying Alkyd	4 - 5	4 - 5

Fastness to Over coating:


5

Suitability For: (+ = Suitable, 0 = Not Suitable)


Baking system	+
Acrylic-isocyanate system	+
Acid curing systems	0
Amine curing systems	0
Air drying systems	+




**Reflectance Curve (Stoving Paint)**  
Full shade (5%) & Reduction (1:16)



**X-ray Diffractogram**



**Transmission Electron Micrograph (TEM)**



**Particle Size Distribution**

**Note:**

Information given in this technical data sheet is based on current knowledge and our laboratory evaluation; it is presented as our opinion without any guarantee. Buyers must carry out their own tests and experiments to determine the suitability and completeness of our products for their use and application.